

Ceramic Zirconia Sheets Blocks



Material	Color	Size	Accuracy	Maximum Temperature	Circular Runout	Perpendicularity	Circularity	Parallelism	Applications	RoHS	Y2O3	FeO3	Na2O	SiO2	TiO2	ZrO2	Density(g/cm3)	Hardness(Kg/mm2)	Bendingstrength(Mpa)	Fracture toughness(Mp a.m- 3/2)	Elastic Modulus(Gpa)
Zirconium Oxide (ZRO2)	White	100x50x20mm	0.008mm	400°C(752F[]	12um	12um	10um	12um	Chemical and medical industry sewage treatment in	Compliant	0.0521	<0.001%	<0.001%	<0.001%	<0.001%	>94%	≥6.0	1100[]1300	>950	8.0[]10.0	210