

Tungsten Carbide outer ring with groove



Material	Bore Dia (d)	Bore Dia Tolerance	Outer Dia (D)	Outer Dia Tolerance	Width (B)	Width Tolerance	Maximum Temperature	Ovality	Perpendicularity	Concentricity	Parallelism	Applications	RoHS	Composition	Density(g/cm3)	Hardness(Kg/mm2)	Bending strength(Mpa)	Ingredients	Porosity and non-combined carbon	Grain size
Tungsten Carbide	30.05mm	+0.00 to -0.03mm	38.00mm	+0.00 to -0.03mm	45.99mm	+0.00 to -0.05mm	950°C	0.005mm	0.01mm	0.01mm	0.01mm	Commonly used on high-precision machining high-pr	Compliant	0.92	14.7	89	2610	0.08	A02 B00 C00	1.6