

Tungsten Carbide Bush



Material	Bore Dia (d)	Bore Dia Tolerance	Outer Dia (D)	Outer Dia Tolerance	Width (B)	Width Tolerance	Maximum Temperature	Ovality	Perpendicularity	Concentricity	Parallelism	Applications	RoHS	Composition	Density(g/cm3)	Hardness(Kg/mm2)	Bending strength(Mpa)	Ingredients	Porosity and non-combined carbon	Grain size
Tungsten Carbide	25.10mm	+0.00 to -0.03mm	32.10mm	+0.00 to -0.03mm	25mm	+0.00 to -0.08mm	950°C	0.005mm	0.01mm	0.01mm	0.01mm	Commonly used on high-precision machining high-pr	Compliant	0.92	14.7	89	2610	0.08	A02 B00 C00	1.6